

Specification Sheet

ISO 12944-5 Ref: (C4D)

Steelwork

New Construction

Environment to ISO12944-2: C4 Environment - Industrial Areas, Chemical Plants and Swimming Pools Etc.

Durability (Life to First Major Maintenance): High Durability: (15-25 years)

Surface Preparation: Blast Clean to Sa2½ BS EN ISO 8501-1:2007 - Surface Profile between 50 - 75μm

| Coat | Product | Product Type | Film Thickness μm | | TSR | Volume | Mixing | Pot Life |
|------|--------------------------------------|----------------------|-------------------|-----|-----------|----------|--------|----------|
| | Product | Product Type | Dry | Wet | (sqm/ltr) | Solids % | Ratio | 23°C |
| 1st | Macropoxy® 400 | Zinc Phosphate Epoxy | 190 | 271 | 3.7 | 70 | 7:1 | 1½ hrs |
| 2nd | Acrolon® 7300 Gloss or Semi-Gloss | Acrylic Polyurethane | 50 | 74 | 13.6 | 68 | 10:1 | 2 hrs |

TSR = Theoretical Spread Rate

| Product | Thinner / | Touch Dry | Recoat | Touch Dry | Recoat | Sag | Colour | Pack | Product Information | |
|---------|--|-----------|--------|-----------|--------|-------------|---------------------|------------|----------------------------------|--|
| Code | Cleansers | 15°C | 15°C | 23°C | 23°C | Tolerance | Range | Size | | |
| 400 | No.2 for Thinning - No.9/13 for Cleaning | 1½ hrs | 5 hrs | 1 hr | 3½ hrs | 400μm d.f.t | Limited Inc, MIO | 20 & 5 ltr | 400 Data Sheets and Information | |
| 7300 | No.15 for Thinning - No. 5 for Cleaning | 4 hrs | 9 hrs | 1 hr | 7 hrs | 150μm d.f.t | Wide Range | 20 & 5 ltr | 7300 Data Sheets and Information | |

D.F.T = Dry Film Thickness

Notes:

- 1 Dry film thicknesses (d.f.t.) quoted are minimum nominal as defined by BS EN ISO 12944-5.
- 2 ISO12944 states that Durability is not a guarantee time. Durability should be considered as the coating design life, where regular minor maintenance should be scheduled to achieve the required life to first major maintenance.
- 3 Stripe coat all edges, welds and areas of difficult access, to ensure full film thickness.
- 4 Subject to shade and method of application, multiple coats of the finish coat may be required to achieve the dft/ full colour obliteration.
- 5 All materials should be obtained from Sherwin-Williams® and must be applied in accordance with our technical data sheets.
- 6 Certification available from Sherwin-Williams® Technical Customer Support.
- 7 For fire protection systems, please contact Sherwin-Williams®.
- 8 This specification is offered as guidance only. To ensure that the most appropriate materials are used, please contact Sherwin-Williams® with the project details.