



ARMORSEAL® 8100

Water Based Epoxy Floor Coating

ArmorSeal® 8100 is the next generation in water based epoxy floor coatings; a two-component polyamine epoxy with excellent chemical and abrasion resistance that is breathable. A LEED 4.2 compliant material that offers improved performance while maintaining ease of application.

Features

- Breathable
- Polyamine Epoxy
- 5+ Hour Potlife
- <50 g/L; 0.42 lb/gal VOC level
- Gloss or Satin Finish
- Water Based
- Apply Direct To Concrete/Damp Concrete

Benefits

- Resists Disbondment From Moisture Vapor
- Excellent Chemical & Abrasion Resistance
- Application Friendly
- Compliant to LEED 4.2
- Final Appearance Options
- Ease of Application and Cleanup
- No Primer Required, Tolerant of Moisture

Recommended Uses

- Industrial Floors
- Warehouse Floors
- Automotive Showrooms
- Bathrooms
- Laboratories
- Assembly & Production Areas
- Commercial Buildings
- Schools
- Hospitals
- Offices
- Retail Facilities
- USDA Inspected Areas



Product Characteristics

Finish: Gloss or Satin
Color: Clear*, Tile Red, Deck Gray, Haze Gray and a wide range of tinted colors using CCE colorants
 Safety Colors Gloss only
 *For clear use UltraDeep Base
Volume Solids: 41% ± 2%, mixed, may vary by color
Weight Solids: 50% ± 2%, mixed, may vary by color
VOC (EPA Method 24): <50 g/L; 0.42 lb/gal, mixed
Mix Ratio: 4:1 by volume

Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns)	5.0 (125)	10.0 (250)
Dry mils (microns)	2.0 (50)	4.0 (100)
~Coverage sq ft/gal (m²/L)	160 (4.1)	320 (8.1)
Theoretical coverage sq ft/gal (m²/L) @ 1 mil / 25 microns dft	656 (16.0)	

NOTE: Brush or roll application may require multiple coats to achieve maximum film thickness and uniformity of appearance.

Drying Schedule @ 7.0 mils wet (175 microns):

	@ 50°F/10°C	@ 77°F/25°C 50% RH	@ 120°F/49°C
To touch:	1 hour	45 minutes	25 minutes
To recoat*:			
minimum:	8 hours	6 hours	3 hours
maximum:	30 days	30 days	30 days
Foot Traffic:		18 hours	
Heavy Traffic:		48 hours	
<i>Drying time is temperature, humidity, and film thickness dependent.</i>			
*If recoating after 30 days, abrade surface first.			
Pot Life:	8 hours	5+ hours	3½ hours
Sweat-in-Time:	None	None	None

Shelf Life:	Part A: 24 months, unopened Part B: 36 months Store indoors at 40°F (4.5°C) to 100°F (38°C)
Flash Point:	>230°F (110°C), Seta Flash, mixed
Reducer/Clean Up:	Water

Performance Characteristics

Substrate*: Concrete
Surface Preparation*: Clean, dry, sound
System Tested*:
 2 cts. ArmorSeal 8100 @ 2.0 - 4.0 mils (50-100 microns) dft

Test Name	Test Method	Results
Abrasion Resistance	ASTM D4060, CS17 wheel, 1000 cycles, 1 kg load	150 mg loss
Adhesion	ASTM D4541	550 psi concrete
Finish	Satin Gloss	15-25 units@ 85° 90+ units @ 60°
Flexibility	ASTM D 522	180° bend 1/8" mandrel
Impact Resistance	ASTM D2794	Direct 100 in.lb. Indirect 80 in.lb.
Pencil Hardness	ASTM D3363	H
WVP Perms (US)	Grains(hr ft ² in Hg)	Gloss – 2.0 Satin – 5.0

A complete line of products. Market expertise. On-time distribution. What else would you expect from a world leader in protective coatings, linings and fire protection?

It starts with a complete line of time-tested, high-performance products and some of the most innovative technologies in the coatings industry. But we know that it takes more than product alone to be a world leader in protective coatings and linings. And so do the customers that rely on us every day as we help them protect their business.

That's where 150 years of coatings industry experience comes in. Add to that a NACE-trained workforce with a combined 3,700 years of experience in corrosion control. The market-specific knowledge that our experts provide to evaluate, recommend and deliver the highest-performance coatings and linings that protect our customers' assets.

It also means that we deliver on time, every time from 4,100 company-owned distribution points worldwide. Leave nothing to chance. Your single source of supply. Sherwin-Williams.



To learn more, visit us at

www.sherwin-williams.com/protective
 or call 1-800-524-5979
 to have a representative contact you.