

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS	
	RESUFLOR™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 GLOSS AND HTS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850
Acetaldehyde	TS	NR	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Acetic Acid - 10%	SD	SD	SD	OK	OK	SD	OK	SD	SD	SD	SD	SD	SD	SD	TS	OK	OK	SD	OK	OK	OK
Acetic Acid - 10-50%	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	TS
Acetic Acid (50%) to Glacial (100%)	SD	SD	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS
Acetic Anhydride	TS	NR	TS	TS	TS	SD	NR	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Acetone - 10%	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Acetone - 100%	SD	NR	SD	TS	TS	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Acetyl Chloride - 100%	TS	NR	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Acrylic Acid - 100%	TS	NR	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Acrylonitrile *	NR	NR	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	TS
Adipic Acid - 25%	OK	OK	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Allyl Alcohol	OK	NR	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Allyl Chloride	TS	NR	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	TS
Alum (Saturated Solution)	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS
Aluminum Bromide	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Aluminum Chloride	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Aluminum Nitrate (Saturated)	TS	NR	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Aluminum Sulfate	TS	NR	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Ammonia (Wet Gas)	OK	OK	OK	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Ammonium Bisulfite	TS	NR	OK	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Ammonium Chloride	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Ammonium Cocoampholyte - 30%	OK	OK	SD	TS	TS	OK	TS	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Ammonium Fluoride	TS	NR	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Ammonium Hydroxide - 20%	OK	OK	OK	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Ammonium Hydroxide - 38%	OK	OK	OK	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Ammonium Lauryl Sulfate - 30%	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

10-26-22_acc

[Accessibility Statement](#)

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS			
	RESUFLOR™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ 3746 SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850	ELLADUR™ 340/5	
Ammonium Nitrate	SD	SD	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	OK	TS	OK	OK	TS	TS	TS	OK	TS		
Ammonium Persulfate	SD	SD	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS		
Ammonium Sulfate	SD	SD	TS	TS	TS	TS	OK	TS	SD	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS		
Ammonium Sulfide	SD	SD	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	SD	TS		
Ammonium Sulfite	SD	SD	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Ammonium Xylene Sulfonate - 40%	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Amyl Acetate	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	
Amyl Alcohol	SD	NR	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	SD	NR	TS	TS	TS	SD	TS	
Aniline	NR	NR	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	TS	NR	TS
Aniline Hydrochloride	OK	NR	TS	TS	TS	SD	TS	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	
Antimony Chloride (Tri)	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	
Aqua Regia	SD	SD	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Arsenous Acid	SD	SD	TS	TS	TS	SD	TS	SD	SD	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	SD	TS
Barium Chloride	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	
Barium Hydroxide	OK	OK	OK	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Barium Sulfate	OK	OK	OK	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Barium Sulfide	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Beer	NR	OK	SD	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	
Benzal Chloride	SD	NR	TS	TS	TS	NR	OK	NR	SD	TS	TS	TS	TS	TS	TS	TS	SD	NR	TS	TS	TS	SD	TS
Benzaldehyde	NR	NR	TS	TS	TS	OK	OK	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Benzene (Benzol)	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	
Benzene Sulfonic Acid - 50-100%	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	
Benzene Thiol	SD	SD	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	
Benzyl Alcohol	TS	NR	SD	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	
Benzoic Acid (Saturated)	OK	SD	SD	TS	TS	OK	TS	OK	OK	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	SD	TS	
Benzoyl Chloride	TS	NR	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS		
	RESUFLOR™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ 3746 SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ TOPCOAT PT 250	RESUFLOR™ MULTIPURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-RESISTANT	FASTOP® TOPCOAT 4090TC	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850	ELLADUR™ 340/5
Benzyl Chloride	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	
Black Liquor (Paper)	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	SD	TS	
Bleach - 5%	OK	OK	SD	OK	OK	OK	SD	OK	OK	SD	SD	SD	SD	OK	TS	SD	OK	OK	OK	OK	OK	
Boric Acid (Saturated)	OK	OK	SD	TS	TS	OK	TS	OK	OK	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Brake Fluid	NR	OK	TS	OK	OK	OK	NR	OK	NR	NR	NR	NR	NR	NR	NR	TS	SD	OK	OK	NR	OK	SD
Brine	OK	OK	SD	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Bromine, Wet Gas	NR	NR	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Bromine, Dry Gas	NR	NR	TS	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Bromine Water - 5%	NR	NR	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Butanol Normal	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS
Butyl Acetate	SD	SD	SD	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS
Butyl Acrylate	SD	NR	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Butyl Amine	SD	NR	SD	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Butyl Carbitol	TS	NR	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Butyl Carbitol Acetate	TS	NR	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Butyl Cellosolve	TS	NR	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Butyl Cellosolve Acetate	NR	NR	TS	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Butyl Ether	SD	SD	SD	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Butyl Acid Levulinic	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Butyric Acid - 100%	SD	SD	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Cadmium Chloride	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Cadmium Plating - Cyanide	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Calcium Bisulfite	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Calcium Chloride	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Calcium Hydroxide	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Calcium Hypochlorite - 5%	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS			
	RESUFLO™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLO™ TOPFLOOR SL23	RESUFLO™ DECO QUARTZ DB23	RESUFLO™ DECO FLAKE SB	RESUFLO™ 3725	RESUFLO™ 3555	RESUFLO™ 3741 NOVOLAC	RESUFLO™ SELF-LEVELING	RESUFLO™ CRN NOVOLAC	RESUFLO™ NOVOLAC TOPCOAT PT 250	RESUFLO™ MULTI-PURPOSE	RESUFLO™ GPE GENERAL PURPOSE	RESUFLO™ UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR® 4844/4850	ELLADUR® 340/5	
Calcium Nitrate	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Calcium Sulfate	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Calcium Sulfite	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	
Caprylic Acid (Octanoic Acid)	TS	NR	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	
Carboxylic Acid (Phenol) - 88%	TS	NR	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	
Carbon Bisulfide (Di) Fumes (Wet)	NR	NR	TS	TS	TS	TS	SD	TS	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	
Carbon Dioxide Gas	OK	OK	SD	TS	TS	SD	TS	SD	OK	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Carbon Tetrachloride	SD	NR	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Castor Oil	OK	OK	SD	TS	TS	SD	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS
Cellosolve	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Cellosolve Acetate	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Chloroacetic Acid - 1-20%	NR	NR	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Chloroacetic Acid - 20-50%	NR	NR	TS	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS
Chloroacetic Acid - 50-100%	NR	NR	TS	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS
Chlorine Dioxide Solution	TS	NR	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS
Chlorine Gas - Dry	OK	SD	SD	TS	TS	SD	NR	SD	OK	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Chlorine Gas - Wet	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Chlorine Water - Saturated	NR	NR	SD	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Chlorobenzene (Mono)	SD	SD	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Chlorobutane	SD	SD	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Chloroform	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Chlorophenol	SD	SD	SD	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Chlorosulfonic Acid	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Chlorotoluene	NR	NR	TS	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Chromic Acid - 10%	SD	SD	SD	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Chrome Plating 20-48 oz/gal	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS		
	RESUFLOR™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 GLOSS AND HTS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850	ELLADUR™ 340/5
Chromic Chloride	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Citric Acid	OK	OK	SD	OK	OK	OK	OK	OK	OK	SD	SD	SD	OK	OK	TS	SD	OK	OK	OK	OK	SD	OK
Copper Chloride	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Copper Nitrate	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS
Copper Plating - Cyanide	SD	SD	SD	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS
Copper Plating - Acid	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS
Copper Sulfate	TS	NR	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	OK	TS
Corn Oil	SD	OK	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD	TS
Cottonseed Oil	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK
Cresol (Cresylic Acid)	NR	SD	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Cresylic Acid	NR	NR	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Cumene	SD	SD	SD	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Cyclohexane	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Cyclohexanone	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Cymene	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Dextrose	SD	OK	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Dibromopropane Phosphate	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Dibutyl Phthalate	OK	SD	TS	TS	TS	OK	TS	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK
Dichloro Acetic Acid - 20%	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Diethanolamine	SD	SD	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Diethylene Chloroformate	SD	SD	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Diethylketone - 100%	NR	NR	TS	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Dimethylaminopropylamine	NR	NR	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Dimethyl Aniline	NR	NR	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	TS	NR
Dimethyl Carbamoyl Chloride	NR	NR	TS	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Dimethyl Carbonyl Chloride	SD	NR	NR	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	TS	NR

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS						POLY-ASPARTIC COATINGS	
	RESUFLOR™ SCREED T-346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-E UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ MC-100 GLOSS GLOSS AND HTS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850
Dimethyl Formamide	NR	NR	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	TS	NR	TS
Dimethyl Sulfoxide	SD	SD	TS	TS	TS	SD	TS	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Dinitro Benzene	SD	SD	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Dinitro Toluene	SD	SD	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Dodecyl Alcohol (Lauryl)	SD	SD	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD	TS
Ethoxy Ethanol	SD	NR	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Ethoxylated Nonyl Phenol	SD	SD	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Ethyl Acetate	NR	SD	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Ethyl Acrylate	NR	NR	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Ethyl Alcohol	SD	NR	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	NR	TS	TS	TS	SD
Ethylamine	NR	NR	TS	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS
Ethyl Bromide	TS	NR	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS
Ethyl Chloride	SD	SD	TS	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Ethyl Chloroformate	SD	SD	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Ethyl Ether	NR	SD	SD	TS	TS	SD	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD
Ethyl Hexyl Acrylate	SD	SD	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Ethylene Dichloride	NR	NR	TS	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Ethylene Glycol	OK	OK	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK
Ethylene Oxide (Dilute)	NR	SD	SD	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK
Ethyl Sulfate	SD	NR	SD	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Ferric Chloride	SD	SD	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Ferric Nitrate	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD
Ferric Sulfate	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Fluosilicic Acid - 25%	NR	NR	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS
Formaldehyde	OK	SD	TS	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Formic Acid	SD	SD	TS	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	SD

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS			
	RESUFLOR™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-E UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ MC-100 GLOSS GLOSS AND HTS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850	ELLADUR™ 340/5
Furfural to 10%	SD	SD	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Gasoline	SD	OK	SD	OK	OK	SD	SD	SD	OK	OK	SD	SD	SD	SD	OK	SD	OK	OK	OK	OK	OK	SD	SD
Aviation	SD	OK	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	TS	SD	TS
Diesel	SD	OK	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Jet Fuel	SD	OK	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Premium Unleaded	SD	OK	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Unleaded	SD	OK	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Glucose	TS	OK	SD	TS	TS	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	OK	TS
Glycerine	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Glycolic Acid to 70%	SD	SD	SD	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Gold Plating (Cyanide)	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS
Grape Juice	TS	OK	SD	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Green Liquor (Paper Industry)	SD	SD	SD	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Heptane	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Hexane	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Hydrazine - 35%	SD	NR	NR	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Hydrazine Hydrate	NR	NR	NR	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Hydriodic Acid - 20%	SD	SD	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Hydrobromic Acid - 20%	SD	SD	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Hydrobromic Acid - 48%	SD	SD	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Hydrochloric Acid - 10%	SD	SD	SD	TS	TS	SD	OK	SD	SD	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	SD	OK	SD	TS
Hydrochloric Acid - 20%	SD	SD	TS	OK	OK	SD	OK	SD	SD	OK	OK	SD	SD	SD	SD	SD	OK	OK	SD	OK	SD	SD	SD
Hydrochloric Acid - 37%	SD	NR	TS	TS	TS	SD	OK	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Hydrofluoric Acid - 1-10% *	OK	NR	TS	TS	TS	OK	NR	OK	OK	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Hydrofluoric Acid - 20% *	SD	NR	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	TS
Hydrofluoric Acid - 21-48%	NR	NR	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	SD	TS

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS						POLY-ASPARTIC COATINGS		
	RESUFLOR™ SCREED T-346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ MC-100 GLOSS GLOSS AND HTS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850	ELLADUR™ 340/5
Hydrofluosilicic Acid - 10%	NR	NR	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS
Hydrofluosilicic Acid - 35%	NR	NR	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS	TS
Hydrogen Peroxide - 30%	NR	NR	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Hydrogen Sulfide Gas	SD	SD	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Hypo (Photographic Solution)	SD	SD	SD	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	TS	OK
Hypochlorous Acid	NR	NR	NR	TS	TS	NR	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	TS	TS	NR
Iodine, Crystals and Vapor	SD	SD	NR	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	TS	OK
Iooctyl Thioglycolate	SD	SD	SD	TS	TS	SD	TS	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	TS	SD
Isophorone	NR	NR	NR	TS	TS	NR	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	TS	TS	NR
Isopropyl Acetate	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	TS	SD
Isopropyl Alcohol	SD	SD	SD	OK	OK	OK	SD	OK	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK
Isopropyl Ether	SD	SD	NR	TS	TS	SD	NR	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	TS	SD
Jet Fuel JP-4	OK	OK	SD	OK	OK	SD	SD	SD	OK	OK	OK	OK	SD	SD	SD	TS	SD	OK	SD	OK	OK	SD	SD
Kerosene	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	SD	OK	TS	TS	TS	SD
Ketchup	TS	OK	OK	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Lactic Acid Concentrated	NR	SD	SD	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	OK	SD	OK	TS	TS	TS	SD
Lard	TS	OK	SD	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	OK
Lauric Acid	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	TS	OK
Lauryl Chloride	SD	SD	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	TS	OK
Lead Acetate	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	OK
Lecithin	OK	OK	SD	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	OK
Levulinic Acid (Saturated)	OK	OK	SD	TS	TS	SD	SD	SD	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	OK
Linseed Oil	OK	OK	SD	TS	TS	TS	SD	TS	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	OK	TS	TS	TS	OK
Lithium Hydroxide - 10%	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Lithium Hydroxide (Saturated)	SD	SD	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Maleic Acid	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	TS	OK

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS						POLY-ASPARTIC COATINGS			
	RESUFLOR™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850	ELLADUR™ 340/5		
Malic Acid	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS		
Mercury and Salts	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS		
Methanol - 100%	OK	SD	SD	TS	TS	OK	NR	OK	OK	TS	TS	TS	TS	TS	NR	OK	SD	SD	TS	TS	SD	TS		
Methyl Acetate	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD	TS		
Methylamyl Alcohol	NR	NR	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD	TS		
Methylene Chloride	NR	NR	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	NR	TS	NR	SD	TS	TS	NR	TS	
Methyl Chloride	NR	NR	NR	TS	TS	SD	NR	SD	NR	TS	TS	TS	TS	TS	TS	TS	NR	SD	TS	TS	TS	NR	TS	
Methyl Ethyl Ketone	SD	SD	NR	OK	OK	OK	SD	OK	SD	SD	SD	SD	SD	SD	SD	OK	SD	OK	OK	SD	OK	SD		
Methyl Oleate	SD	SD	SD	TS	TS	SD	OK	SD	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Methyl Isobutyl Ketone	NR	NR	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Milk - Fresh and Sour	TS	OK	SD	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS	TS	TS	
Mineral Spirits	OK	OK	SD	OK	OK	SD	SD	SD	OK	OK	OK	OK	OK	OK	OK	TS	SD	OK	OK	OK	OK	SD	OK	
Molasses	TS	OK	OK	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Muratic Acid	OK	OK	SD	TS	TS	SD	SD	SD	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	TS	OK	TS	
Naphtha - Aliphatic	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	
Naphtha - Aromatic (Coal Tar)	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	
Naphthalene (In Benzene)	TS	NR	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	
Naphthenic Acid	NR	NR	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Nickel Plating, Bright	OK	OK	TS	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS
Nitric Acid - 5%	SD	OK	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Nitric Acid - 10%	SD	SD	TS	SD	SD	OK	SD	OK	SD	SD	SD	SD	SD	NR	SD	OK	SD	SD	NR	NR	SD	NR	SD	
Nitric Acid - 25%	NR	NR	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Nitric Acid - 40%	NR	NR	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Nitric Acid - 60%	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Nitric Acid - 73%	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	
Nitric Acid - 89%	NR	NR	TS	TS	TS	NR	NR	NR	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS	
	RESUFLOR™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOP™ GPE GENERAL PURPOSE	RESUFLOP™ UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850
Nitrilotriethanol	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Nitrobenzene	NR	NR	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Nitromethane	NR	NR	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Octanol	SD	SD	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	OK
Oils	OK	OK	SD	TS	TS	NR	SD	NR	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Sour Crude Petroleum	SD	OK	SD	TS	TS	NR	SD	NR	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Animal	NR	OK	SD	TS	TS	NR	SD	NR	NR	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Mineral	NR	OK	SD	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Vegetable	NR	OK	SD	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Oleic Acid	SD	SD	SD	TS	TS	SD	TS	SD	SD	TS	TS	TS	TS	TS	TS	SD	TS	OK	OK	TS	OK
Oxalic Acid (Saturated)	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Para Xylene	SD	NR	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD
Pelargonic Acid	OK	OK	TS	TS	TS	OK	TS	OK	OK	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	SD
Pentachloroethane	SD	SD	SD	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	SD
Perchloric Acid - 30%	SD	SD	TS	TS	TS	TS	NR	TS	SD	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Perchloroethylene	SD	SD	TS	TS	TS	SD	NR	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Phenol - 5%	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Phenol - 85%	NR	NR	TS	TS	TS	TS	NR	TS	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Phenol Sulfonic Acid - 65%	SD	NR	NR	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	SD
Phosphoric Acid - 20%	SD	OK	SD	SD	SD	OK	SD	OK	SD	SD	SD	SD	SD	SD	SD	SD	SD	OK	SD	SD	SD
Phosphoric Acid - 50%	SD	OK	NR	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	NR	TS	SD	OK	TS	TS
Phosphoric Acid - 85%	SD	NR	NR	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	SD
Phosphorous Oxychloride	NR	NR	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Phosphorous Trichloride	NR	NR	TS	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Picric Acid - 10% (In Alcohol) *	NR	NR	TS	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Polyacrylic Acid - 50%	OK	OK	SD	TS	TS	SD	TS	SD	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS			
	RESUFLOR™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ MC-100 GLOSS GLOSS AND HTS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850	ELLADUR™ 340/5
Potassium Acetate	OK	SD	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Bichromate	NR	SD	SD	TS	TS	SD	OK	SD	NR	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Bromide	SD	SD	SD	TS	TS	SD	OK	SD	SD	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Carbonate - 25%	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Chlorate	SD	OK	SD	TS	TS	OK	OK	OK	OK	SD	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Chloride	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Cyanide	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Fluoride	OK	OK	SD	TS	TS	SD	TS	SD	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Hydroxide - 10%	OK	OK	SD	TS	TS	SD	OK	SD	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Hydroxide - 50%	SD	OK	SD	TS	TS	SD	OK	SD	SD	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Nitrate	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Permanganate	SD	SD	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	
Potassium Persulfate	SD	SD	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Potassium Sulfate	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Propanediol	OK	SD	TS	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Propionic Acid - 100%	NR	NR	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	
Propylene Glycol	SD	SD	TS	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Pyridine	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	
Rayon Spin Liquor	SD	SD	SD	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Salicyaldehyde	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Salicylic Acid	SD	SD	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Salt Brine	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Silicon Tetrachloride	SD	SD	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Silver Nitrate	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	
Skydrol	SD	SD	TS	OK	OK	OK	NR	OK	SD	SD	NR	NR	SD	NR	SD	NR	OK	OK	OK	OK	OK	NR	
Sodium Acetate	SD	SD	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS			
	RESUFLOR™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850	ELLADUR™ 340/5	
Sodium Bicarbonate	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Bisulfate	OK	OK	SD	TS	TS	SD	OK	SD	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Bisulfite	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Bromate	OK	OK	SD	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Carbonate (Saturated)	OK	OK	SD	TS	TS	NR	OK	NR	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Chloride	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	OK	TS	OK	OK	TS	TS	OK	TS	
Sodium Chlorite (Saturated)	SD	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	
Sodium Chromate	OK	OK	SD	TS	TS	OK	SD	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Chlorate	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Cyanide - 15%	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Dichromate	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Fluoride	SD	SD	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Hydrosulfide - 45%	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	OK	SD	TS	TS	TS	OK	TS	
Sodium Hydroxide - 10%	OK	OK	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	
Sodium Hydroxide - 50%	SD	OK	SD	OK	OK	OK	OK	OK	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	
Sodium Hypochlorite - 3%	SD	SD	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Sodium Hypochlorite - 17%	NR	SD	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS	
Sodium Lauryl Sulfate - 20%	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Sodium Oxalate	OK	OK	TS	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Sodium Peroxide - Peroxide Bleach	SD	SD	SD	TS	TS	OK	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Sodium (Acid) Phosphate	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS	
Sodium Phosphate (Tri)	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Sodium Polymethacrylate	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Sodium Sulfate	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Sodium Sulfide (Saturated)	NR	SD	SD	TS	TS	OK	OK	OK	NR	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Sodium Sulfite	NR	SD	SD	TS	TS	OK	OK	OK	OK	NR	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS			
	RESUFLOR™ SCREED T346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-E UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850	ELLADUR™ 340/5	
Sodium Tartrate	SD	SD	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Sodium Thiosulfate (Hypo)	SD	SD	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS	
Soybean Oil	TS	OK	SD	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	
Stannic Chloride	NR	SD	SD	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Stannous Chloride	NR	SD	SD	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Stearic Acid	OK	OK	SD	TS	TS	SD	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Styrene	NR	NR	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Sugar	TS	OK	SD	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Sulfamic Acid - 25%	SD	SD	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Sulfite Liquor (Paper Industry)	SD	SD	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Sulfur Dioxide (Wet)	SD	SD	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Sulfur Trioxide (Wet)	SD	SD	TS	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Sulfuric Acid - 10%	SD	OK	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD	TS
Sulfuric Acid - 25%	SD	OK	TS	SD	SD	OK	SD	OK	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD	SD
Sulfuric Acid - 50%	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	SD	SD	TS	TS	SD	TS
Sulfuric Acid - 70%	SD	NR	TS	TS	TS	OK	NR	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	TS	SD	TS
Sulfuric Acid - 90-98%	NR	NR	NR	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	NR	NR	TS	TS	TS	NR	TS
Tall Oil	SD	OK	TS	TS	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS	TS
Tartaric Acid	SD	SD	SD	TS	TS	OK	OK	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK	TS
Tetrachloroethane	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Tetrachloroethylene	TS	NR	TS	TS	TS	OK	SD	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Tetrahydrofuran	TS	NR	TS	TS	TS	OK	TS	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Tetrahydrofurfuryl Alcohol	TS	NR	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Thionyl Chloride	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS	TS
Thionyl Chloride - Water Solution *	TS	NR	TS	TS	TS	OK	NR	OK	TS	TS	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS	TS
Toluol	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD	TS

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended

	MORTAR SYSTEMS		BROADCAST SYSTEMS		EPOXY COATINGS										URETHANE COATINGS					POLY-ASPARTIC COATINGS	
	RESUFLOR™ SCREED T-346	FASTOP® (NO TOPCOAT)	RESUFLOR™ TOPFLOOR SL23	RESUFLOR™ DECO QUARTZ DB23	RESUFLOR™ DECO FLAKE SB	RESUFLOR™ 3725	RESUFLOR™ 3555	RESUFLOR™ 3741 NOVOLAC	RESUFLOR™ SELF-LEVELING	RESUFLOR™ CRN NOVOLAC	RESUFLOR™ NOVOLAC TOPCOAT PT 250	RESUFLOR™ MULTI-PURPOSE	RESUFLOR™ GPE GENERAL PURPOSE	RESUFLOR™ UV-E UV-RESISTANT	FASTOP® 4090TC TOPCOAT	RESUTILE™ 4638	RESUTILE™ 4685	RESUTILE™ MC-100 GLOSS GLOSS AND SATIN	RESUTILE™ HPS 100 GLOSS AND HTS 100 SATIN	RESUTILE™ SDU STATIC DISSIPATIVE	ELLADUR™ 4844/4850
Toluene Sulfonic Acid	NR	NR	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Toluidine	NR	NR	TS	TS	TS	OK	TS	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Triethylamine	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS	TS
Triethylenetetramine	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Triethyl Phosphite	NR	NR	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	OK	TS	TS	TS	TS
Trichloroacetic Acid - 20%	SD	SD	TS	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Trichlorobenzene (1,2,4-)	SD	SD	TS	TS	TS	SD	SD	SD	SD	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD
Trichloroethane	NR	NR	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Trichloroethylene	NR	NR	TS	TS	TS	OK	SD	OK	NR	TS	TS	TS	TS	TS	TS	TS	SD	TS	TS	TS	TS
Tricresyl Phosphate - 100%	NR	NR	TS	TS	TS	SD	OK	SD	NR	TS	TS	TS	TS	TS	OK	TS	SD	OK	TS	TS	SD
Trisodium Phosphate (Saturated)	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	SD	OK	TS	TS	TS	SD
Turpentine	NR	NR	TS	TS	TS	SD	SD	SD	NR	TS	TS	TS	TS	TS	TS	TS	SD	SD	TS	TS	SD
Urea Solutions	OK	OK	SD	TS	TS	OK	OK	OK	OK	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Vinegar	SD	SD	SD	TS	TS	OK	SD	OK	SD	TS	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	OK
Vinyl Chloride	NR	NR	TS	TS	TS	OK	NR	OK	NR	TS	TS	TS	TS	TS	TS	TS	TS	NR	TS	TS	TS
Water, Distilled & Demineralized	SD	OK	SD	OK	OK	OK	OK	OK	SD	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK	OK
Water, Deionized	SD	OK	SD	OK	OK	SD	OK	SD	SD	OK	OK	OK	OK	OK	OK	OK	SD	OK	OK	OK	OK
White Liquor (Paper Industry)	NR	SD	SD	TS	TS	SD	OK	SD	NR	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK
Wine	TS	OK	SD	TS	TS	SD	TS	SD	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS	TS
Xylool	NR	SD	TS	OK	OK	SD	SD	SD	NR	OK	OK	SD	SD	SD	SD	TS	SD	SD	OK	OK	SD
Zinc Plating - Acid Fluoborate	SD	SD	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK
Zinc Plating - Cyanide	SD	SD	SD	TS	TS	OK	TS	OK	SD	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK
Zinc Plating - Acid Sulfate	NR	SD	SD	TS	TS	SD	TS	SD	NR	TS	TS	TS	TS	TS	TS	OK	OK	TS	TS	TS	OK

THE SHERWIN-WILLIAMS DIFFERENCE

Sherwin-Williams High Performance Flooring delivers world-class industry subject matter expertise, unparalleled technical and specification service, and unmatched regional commercial team support to our customers around the globe.

OK = Recommended for exposure not to exceed 72 hrs prior to cleaning

*Requires additional considerations - contact Technical Services

SD = Splash/Spillage Daily

TS = Contact Tech Service Department

NR = Not Recommended